

SCHEMA TECNICA
TECHNICAL CARD

Articolo / Article / Tkanina	Adamantio
Codice Articolo / Article Code / Kod tkaniny	8604
Composizione / Composition / Kompozycja	100 % PL
Peso Gr/mtl / Weight Grs/lmt / Waga gr/mtb	640
Altezza cm / Width cms / Szeroko cm	140

Odporno na cieranie

Test Martindale Colour degradation after 3000 rubs: 4/5
 UNI EN ISO 12947 - 2 **>100.000** Giri / Rubs / **Cykli** End Point
 EN 14465, appendix A

Solidità Luce / Colour Fastness to light / **Odporno kolorów na wiatło**

UNI EN ISO 105-B02 **4/5**
 Blue Scale 1/8

Solidità Sfregamento / Colour Fastness to rubbing / **Odporno kolorów na pocieranie**

UNI EN ISO 105-X12 **4** Secco / Dry / **Sucho**
 Gray Scale 1/5 **3/4** Umido / Wet / **Mokro**

Odporno na Pilling

Test Pilling Degradation average photographic scale 1/5: **4**
 UNI EN ISO 12945-2 **4** a 2000 giri / at 2000 revs

Scorrimento cuciture / Seams Slippage

UNI 9743/90 Scorrimento / Slippage 6 mm **> N** Ordito su trama / Warp over weft
 Scorrimento / Slippage 6 mm **> N** Trama su ordito / Weft over warp

Resistenza alla lacerazione / Tearing strength

UNI EN 29073/4 **N** Ordito / Warp
N Trama / Weft

Manutenzione / Maintenance



Note/Notes: **Dimensional stability to dry washing (UNI EN ISO 3175)**
Stabilno wymiaru przy praniu chemicznym (UNI EN ISO 3175)
 warp / w tek: +/- 1 % weft / osnowa: +/- 1 %
Dimensional stability to washing (UNI EN ISO 6330)

Stabilno wymiaru przy praniu wodnym (UNI EN ISO 6330)

warp / w tek: +/- 2 % węft / osnowa: +/- 2 %

* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI S.P.A. - VIA PERUGIA, 29 - 59013 MONTEMURLO (PO) ITALY

TEL.: +39/0574-79711 - FAX: +39/0574-798141 - E-MAIL: info@italvelluti.it